

QC CURING COMPOUNDS

Product Name	Carrier Description	Solids Content	VOC Content Compliant*	Gloss	Recommended Surfaces	Unique Characteristics	Coverage Per Coat / Square Foot	Coefficient of Friction (COF)
<i>QC Clear Cure</i>	Water Film forming acrylic	18%	< 250 grams/liter Compliant in most regions	85 - Medium Gloss	Colored Concrete, Gray Concrete and Overlays	Meets or exceeds ASTM C309 and ASTM C156 at 300 square feet per gallon, variety of colors	400-500 porous 800+ dense	>0.8 dry
<i>QC Color Cure</i>	Water Film forming acrylic	30%	< 250grams/liter Compliant in most regions	<85 – Low to Medium Gloss	Colored Concrete, Gray Concrete and Overlays	Meets or exceeds ASTM C309 and ASTM C156 at 300 square feet per gallon, moderate color enhancement	300-400 porous 400-600 dense	>0.8 dry
<i>QC Color Wax</i>	Water Film forming acrylic	45%	< 250 grams/liter Compliant in most regions	<40 - Satin	Colored Concrete, Gray Concrete and Overlays	High quality, tinted to a wide variety of colors, ease of use, all acrylic formulation, contains no waxes	300-500 porous 400-600 dense	>0.5 dry
<i>QC Cure and Seal SB CA VOC Std.</i>	Solvent Film forming modified acrylic	25%	< 350 grams/liter Compliant in most Air Control Districts	93 – High Gloss	Curing: Colored Concrete and Gray Concrete Seal: Colored Concrete, Gray Concrete, Stamped Concrete and Stained Concrete	Intended as a curing compound for fresh concrete. Moderate color enhancement, breathable, non-yellowing. Formulated with a UV inhibitor to meet ASTM C1315 and C309	100-200 porous 300 dense	>0.5 dry
<i>QC Sure Cure</i>	Impregnating Internal silicate cure	N/A	< 50 grams/liter Compliant	N/A	This product is ONLY for gray concrete that is going to be stained!!	Intended as a curing compound for fresh gray concrete. Does not meet ASTM C1315 or C309	500-600	>0.5 dry

**Before use, consult state and local regulations to verify product VOC compliance for your area.*

QC FINISH COATINGS

Product Name	Carrier Description	Solids Content	VOC Content Compliant*	Gloss	Recommended Surfaces	Unique Characteristics	Coverage Per Coat / Square Foot	Coefficient of Friction (COF)
<i>QC Interior Floor Finish</i>	Water Film forming wax modified acrylic	25%	< 250 grams/liter Compliant in most regions	90 – High Gloss	Interior only: Colored Concrete, Gray Concrete, Stained Concrete and Overlays	Intended as a breathable high-gloss maintenance finish over QC sealers and high performance coatings	800-1,000 per 1st coat on dense concrete. Up to 1,800 per subsequent coats on dense concrete	>0.6 dry
<i>QC Natural Beauty</i>	Water Film forming wax modified acrylic	19%	< 250 grams/liter Compliant in most regions	32 - Satin	Interior only: Colored Concrete, Gray Concrete, Stained Concrete and Overlays	Intended as a breathable low-gloss maintenance finish over QC sealers and high performance coatings	800-1,000 per 1st coat on dense concrete. Up to 1,800 per subsequent coats on dense concrete	>0.6 dry

**Before use, consult state and local regulations to verify product VOC compliance for your area.*

QC SPECIALTY PRODUCTS

Product Name	Carrier Description	Solids Content	VOC Content Compliant*	Gloss	Recommended Surfaces	Unique Characteristics	Coverage Per Coat / Square Foot	Coefficient of Friction (COF)
<i>QC Con-Clean</i>	Water Detergent modified mineral acid	N/A	< 25 grams / liter Compliant	N/A	Concrete, Masonry, QC Concrete Resurfacer and QC Thin Pave NI	Intended for surface preparation and cleaning prior to staining. Also removes efflorescence and scale Diluted with water 20:1	Diluted 4,000 sf/gallon	N/A
<i>QC Concrete Degreaser & Neutralizer</i>	Water Alkaline soap	N/A	< 25 grams / liter Compliant	N/A	Concrete, Masonry, QC Concrete Resurfacer and QC Thin Pave NI	Intended for neutralizing surfaces that have been chemically stained. Also cleans oil and grease from concrete / masonry surfaces Diluted with water 20:1	Diluted 4,000 sf/gallon	N/A
<i>QC Patina Stain Extender Dilution Liquid</i>	Water Clear chemical stain	N/A	0 grams/liter	N/A	Concrete, Masonry, QC Concrete Resurfacer and QC Thin Pave NI	Clear liquid intended to diluted QC Patina Stain. Also removes QC Patina Stain from unwanted areas	N/A	N/A
<i>QC Flattening Agent</i>	Dry Modified Silica Fume	N/A	N/A	N/A	Colored Concrete, Stamped Concrete, Overlays and Stained Concrete	Intended to reduce the level of gloss of any water or solvent based QC sealer	16 oz./gallon	N/A
<i>QC Sure Trac & Extra Sure Trac</i>	Dry Ground polymers	N/A	N/A	N/A	Colored Concrete, Stamped Concrete, Overlays and Stained Concrete	Intended to increase the coefficient of friction of any QC sealer or Finish Coating.	9 oz./gallon	Increases by 0.2 to 0.5
<i>QC Seal Strip</i>	Water Chemical stripper	N/A	0 grams/liter	N/A	Colored Concrete, Stamped Concrete, Overlays and Stained Concrete	Water based pH neutral stripper for removing QC sealers	60-100 sf/gallon	N/A
<i>QC Interior Floor Strip</i>	Water Chemical stripper	N/A	0 grams/liter	N/A	Colored Concrete, Stamped Concrete, Overlays and Stained Concrete	Intended to remove QC Interior Floor Finish or QC Natural Beauty without effecting the base coat sealer below	1,000 sf/gallon	N/A
<i>QC Floor Cleaner</i>	Water pH neutral detergent	N/A	< 25 grams / liter Compliant	N/A	Colored Concrete, Stamped Concrete, Overlays and Stained Concrete	Intended for cleaning any surface sealed with a QC sealer or finish coating. Intended to be diluted depending on type of soil	5,000 to 40,000 sf/gallon	N/A

**Before use, consult state and local regulations to verify product VOC compliance for your area.*